

## TECHNICAL SPECIFICATION: OXYDECOR® COPPER

Carry out of Oxydecor® Copper, decorative coating that recreates the appearance of copper

Cleaning of the surface and application with roller or brush of **Deco Primer Finish** Isoplam® in a ratio of about 0.15 L/m<sup>2</sup>.

Application with roller of one coat of Isoplam® **Oxyzinc Powder** + Isoplam® **Oxyzinc Liquid** in a ratio of about 0.29 L/m<sup>2</sup>. Uneven application of Isoplam® **Oxyrust Paint** with Isoplam® **Plastic trowel** in a ratio of about 0.22 L/m<sup>2</sup>.

Irregular spraying of Isoplam® **Oxyrust Oxidant** at a rate of about 0.10 L/m<sup>2</sup> and, subsequently, of Isoplam® **Oxyrust Activator** at a rate of about 0.12 L/m<sup>2</sup>, uniformly over the entire surface, with an Isoplam® **Acid Pump**, in order to block the oxidation cycle.

Roller or spray application of Isoplam® water-based **Oxyrust Protection** at a rate of about 0.14 L/m<sup>2</sup> or Isoplam® matt polyurethane protective resin **Plam Pol Water** at a rate of about 0.20 L/m<sup>2</sup>.

The price includes: the protection of parts not affected by the processing, the supply and transportation of materials to the construction site, the equipment and machinery for carrying out the work.

For a total of ..... m<sup>2</sup> at the price of € ...../m<sup>2</sup>

### Isoplam S.r.l.

Via E. Mattei 4 - 31010 Maser (TV) Italy  
Tel: +39 0423 925023 - Mail: info@isoplam.it  
Pec: isoplamsrl@pec.it - Web: www.isoplam.it

Reg. Imp. / Partita IVA IT02432450266 | R.E.A. n. TV-210216 | Cap. Soc. 12.000,00 i.v.  
Iscritta c.c.i.a.a. 02432450266 di Treviso in data 19.02.1996  
Società soggetta all'attività di direzione e coordinamento di MDF Holding