

TECHNICAL SPECIFICATION: PAVILUX® OVERLAY

Carry out of continuous indoor/outdoor industrial low thickness concrete flooring

Accurate cleaning and roughening of the existing floor in seasoned cls, made according to UNI EN 206-1. Application of Isoplam® Cement Primer with Isoplam® Broom.

Laying, in a thickness of about 2-3 cm, of the Isoplam® Pavilux Overlay dough according to the colour chosen by the Works Management based on the Isoplam® Colour Chart, at a rate of about 20 Kg/m²/cm thickness and processing with Isoplam® Screed.
Roughing of fresh concrete with the aid of Isoplam® Power Trowel with Isoplam® Flat shoe power trowel Blades or

Isoplam® Galvanized float pan.

In the case of internal flooring, smooth with **Power trowel** with mounted **Flat finish blades**.

Application of Isoplam[®] Anti-evaporation treatment in a ratio of about 0.2 L/m² for the protection of the flooring

Execution of the control joints with Isoplam® Diamond disc and laying of Isoplam® expanded polyethylene Backer Rod.

Laying of Isoplam® Nylon coupled with Isoplam® Nonwoven Fabric wetted against the rapid drying of the flooring. After drying the cls, apply Isoplam [®] Plam Sigil or Isoplam [®] Colored Silicone.

Floor washing and application of Isoplam® protection: consult the Isoplam® Technical Department for the choice of the most suitable product.

The price includes: the protection of parts not affected by the processing, the supply and transportation of materials to the construction site, the equipment and machinery for carrying out the work.

For a total of.	m ² at the	price of €	/m²
i oi a totai oi.	III at the	price or e	