

TECHNICAL SPECIFICATION: SURFACE ACIDIFICATION

Realization of dye acidification treatment on Isoplam[®] concrete surfaces

Preparation of the concrete base with Isoplam[®]'s **Deco Nuvolato** Light Gray or Medium Gray, seasoned and free of rising damp, by washing it with acid **Plam Apripori** Isoplam[®].

Application of **Plam Acid** Isoplam[®] at a rate of approx. 0.2 L/m² with an Isoplam[®] **Acid Pump** in the shade chosen by the construction manager based on the Isoplam Colour Chart. Leave the product to act for approximately 4 hours.

Possible reapplication of Plam Acid.

Application of neutraliser for acids **Neutra Clean Liquid** Isoplam[®] and thorough washing of the flooring with Isoplam[®] **Monobrush** or **Washer Dryer**.

Application of Isoplam[®] protective coating: consult the Isoplam[®] Technical Department for the choice of the most suitable product.

The price includes: the protection of parts not affected by the processing, the supply and transportation of materials to the construction site, the equipment and machinery for carrying out the work.

For a total of m² at the price of €/m²

Isoplam S.r.l.

Via E. Mattei 4 - 31010 Maser (TV) Italy

Tel: +39 0423 925023 - Mail: info@isoplam.it

Pec: isoplamsrl@pec.it - Web: www.isoplam.it

Reg. Imp. / Partita IVA IT02432450266 | R.E.A. n. TV-210216 | Cap. Soc. 12.000,00 i.v.
Iscritta c.c.i.a.a. 02432450266 di Treviso in data 19.02.1996

Società soggetta all'attività di direzione e coordinamento di MDF Holding