

## TECHNICAL SPECIFICATION: SKYSENSE

### Implementation of a low-thickness (2 mm) slightly marbled internal coating.

Thorough cleaning of the existing surface in cured and reinforced concrete constructed according to UNI EN 206-1.  
Application of **Skyprimer** Isoplam® (at a rate of approximately 1.1 kg/m<sup>2</sup>), a two-component epoxy to be dusted with Quartz 0.6-1.2 Isoplam® (at a rate of approximately 3 kg/m<sup>2</sup>), washed, and dried.  
Application of the first layer composed of **Plam Hardening** Isoplam® powder (at a rate of approximately 1.5 kg/m<sup>2</sup>) mixed with **Skybond** Isoplam® liquid binder (at a rate of approximately 0.4 L/m<sup>2</sup>), evenly troweled on the surface with an Isoplam® **Steel Trowel**, until achieving a suitable thickness, according to the color chosen by the Site Management based on the Isoplam® **Color Chart**.  
Application of the second layer composed of **Plam Hardening** Isoplam® powder (at a rate of approximately 1 kg/m<sup>2</sup>) mixed with **Skybond** Isoplam® liquid binder (at a rate of approximately 0.2 L/m<sup>2</sup>), troweled on the surface with an Isoplam® **Steel Trowel** and finished with an Isoplam® **Squeegee**.  
Processing and smoothing with Isoplam® **Mechanical Troweling Machine** with **Pvc Smoothing Blades** Isoplam® mounted and with the use of **E Red** Isoplam® antievaporant to counteract rapid surface drying.  
Sanding with Isoplam® **Monobrush** with Isoplam® **Sandpaper Disc**, grain 120.  
Execution of any control joints, reproducing the filling present in the underlying surface, and sealing with Colored Isoplam® **Silicone**.  
Application of transparent protective Isoplam®: consult the Isoplam® Technical Office for the selection of the most suitable product.  
The price includes: protection of parts not involved in the processing, supply and transport of materials to the construction site, equipment, and machinery for the execution of the work.

**For a total of ... m<sup>2</sup> at a cost of € .../m<sup>2</sup> + VAT.**

#### Isoplam S.r.l.

Via E. Mattei 4 - 31010 Maser (TV) Italy  
Tel: +39 0423 925023 - Mail: [info@isoplam.it](mailto:info@isoplam.it)  
Pec: [isoplamsrl@pec.it](mailto:isoplamsrl@pec.it) - Web: [www.isoplam.it](http://www.isoplam.it)

Reg. Imp. / Partita IVA IT02432450266 | R.E.A. n. TV-210216 | Cap. Soc. 12.000,00 i.v.  
Iscritta c.c.i.a.a. 02432450266 di Treviso in data 19.02.1996  
Società soggetta all'attività di direzione e coordinamento di MDF Holding