

## TECHNICAL SPECIFICATION: TERRAZZOVERLAY™

Implementation of a low-thickness (4-8 mm) polished internal/external coating with a micro-Venetian effect.

Thorough cleaning of the suitable existing substrate.

Installation of levigable Plam profil profiles Isoplam® to create control joints, bringing to the surface those existing in the screed.

Application of **Deco Epox W Bi** Isoplam® as an absorption leveling agent for the support.

Application of **Skyprimer** Isoplam® (at a rate of approximately 1 kg/m<sup>2</sup>), a two-component epoxy to be dusted with Quartz 0.6-1.2 Isoplam® (at a rate of approximately 3 kg/m<sup>2</sup>), washed, and dried.

Application, with a thickness ranging from 6 to 10 mm defined with an adjustable **Racla** Isoplam®, of the mixture of **Terrazzo Bond** Isoplam® (0.41 L/m<sup>2</sup>/mm thickness) + **Terrazzo Mix** Isoplam® (0.82 kg/m<sup>2</sup>/mm thickness) + Marble (1.08 kg/m<sup>2</sup>/mm thickness), chosen by the Site Management according to the Isoplam® **Color Chart** and the Isoplam® Aggregates Palette, and worked with Isoplam® **Trowel**.

Smoothing of the surface with Isoplam® **Steel Trowel**, applying **E Red** Isoplam® to prevent excessive evaporation during processing.

Homogenization of the surface with Isoplam® **Stencil Roller**.

Sanding of the surface with Isoplam® **Sander**, using Isoplam® **Abrasive Discs**, and filling any small holes.

Polishing the surface with Isoplam® **Polishing Discs** for a glossy indoor effect or brushing with Isoplam® **Brush Discs** for a non-slip outdoor effect.

Application of Isoplam® protective coating: consult the Isoplam® Technical Office for the selection of the most suitable product.

The price includes: protection of parts not involved in the processing, supply and transport of materials to the construction site, equipment, and machinery for the execution of the work.

**For a total of ... m<sup>2</sup> at a cost of € .../m<sup>2</sup> + VAT.**

### Isoplam S.r.l.

Via E. Mattei 4 - 31010 Maser (TV) Italy  
Tel: +39 0423 925023 - Mail: info@isoplam.it  
Pec: isoplamsrl@pec.it - Web: www.isoplam.it

Reg. Imp. / Partita IVA IT02432450266 | R.E.A. n. TV-210216 | Cap. Soc. 12.000,00 i.v.  
Iscritta c.c.i.a.a. 02432450266 di Treviso in data 19.02.1996  
Società soggetta all'attività di direzione e coordinamento di MDF Holding