

SPECIFICATIONS PLAM DENSIFIER

Sodium-based densifying treatment for internal cementitious concrete surfaces.

In the presence of concrete flooring, after a curing period of 7 days, the surface shall be washed using **Plam Apripori** acid, or alternatively Wow neutral detergent, or Plam Super Cleaner Isoplam[®] heavy-duty degreasing detergent, followed by thorough rinsing.

Application of Plam Densifier Isoplam[®], at a rate of approximately 0.2–0.3 L/m², using Isoplam[®] **white sponge disc** mounted on the Isoplam[®] single-disc machine, keeping the surface wet and continuously working the product into the substrate for at least 30 minutes.

Thorough rinsing of the surface using a pressure washer or Isoplam[®] scrubber dryer, followed by removal of excess water with Isoplam[®] floor squeegee.

Application of one coat of **Antiolio Isoplam[®]** (approx. 0.1 L/m²), **Metallic Wax Isoplam[®]** (approx. 0.03 L/m²), or Plam Poly Wax Isoplam[®] (approx. 0.03 L/m²).

The price includes: protection of adjacent areas not involved in the works, supply and transport of materials to site, as well as all equipment and machinery required for proper execution of the works.

For a total of m² at a cost of €/m² + VAT.

Isoplam S.r.l.

Via E. Mattei 4 - 31010 Maser (TV) Italy
Tel: +39 0423 925023 - Mail: info@isoplam.it
Pec: isoplamsrl@pec.it - Web: www.isoplam.it

Reg. Imp. / Partita IVA IT02432450266 | R.E.A. n. TV-210216 | Cap. Soc. 12.000,00 i.v.
Iscritta c.c.i.a.a. 02432450266 di Treviso in data 19.02.1996
Società soggetta all'attività di direzione e coordinamento di MDF Holding